

AAV TEST BS EN 1097-8:2009

Standard test sand to BS EN 1097-8:2009 - Determination of the polished stone value Annex A Determination of aggregate abrasion value (AAV).

Description: Washed, dried and graded Leighton Buzzard silica sand.

Particle Shape: Rounded to sub-rounded.

Colour: White variety (silver grey to pale buff).

Particle Size: Between 850um and 300um.

Grading: 100% passing 850µm * 75% min passing 600um 25% max passing 425um 0% passing 300um *

* Note: If less than 0.1% retained on an 850 um sieve and less than 0.1% passes 300um the material shall be deemed to comply with the standard

Packaging: Supplied in 20kg bags

Manufactured, produced and processed by
DB Group (Holdings) Ltd, Wellington Way, Bourn Airfield, Cambridge, CB23 2TQ

Tel: 01954 780687

W: www.dbgholdings.com

E: sales@dbgholdings.com